



**SHERWIN
WILLIAMS.**



107.10 PREPRITE® BLOCK FILLER INTERIOR/EXTERIOR LATEX B25W25

<u>CHARACTERISTICS</u>	<u>APPLICATION</u>	<u>SURFACE PREPARATION</u>
<ul style="list-style-type: none"> Allows topcoat on concrete block to be smooth and uniform Effective on above-grade, unpainted masonry surfaces <p>Use on unpainted:</p> <ul style="list-style-type: none"> Masonry Concrete Cement Flat Surfaced Concrete Block <p>Color: Off White</p> <p>Coverage: 75-125 sq ft/gal @ 16 mils wet; 8 mils dry</p> <p>Drying Time, @ 77°F, 50% RH: temperature and humidity dependent</p> <p>Touch: 2 hours Recoat with latex based: 18 hours Recoat with solvent based: 48 hours</p> <p>Flash Point: N/A</p> <p>Finish: 0-5 units @ 85°</p> <p>Vehicle Type: Vinyl Acrylic</p> <p>B25W25</p> <p>VOC (less exempt solvents): 45 g/L; 0.38 lb/gal</p> <p>Volume Solids: 48 ± 2%</p> <p>Weight Solids: 68 ± 2%</p> <p>Weight per Gallon: 13.5 lb</p> <p>SQAQMD, CARB and OTC Compliant</p>	<p>Masonry, Concrete, Cement, Block 1 ct. PrepRite Block Filler 2 cts. Appropriate topcoat</p> <p>Recommended Architectural Topcoats A-100 Exterior Latex Loxon Masonry Coating SuperPaint Exterior Duration Exterior</p> <p>Classic 99 Interior Duration Home ProClassic Interior ProMar Interior SuperPaint Interior</p> <p>Recommended Industrial Topcoats DTM Acrylic Enamel Industrial Enamel Metalatex Semi-Gloss Water Based Catalyzed Epoxy</p> <p>Apply at temperatures above 50°F. No reduction necessary.</p> <p>Brush - Use a nylon/polyester brush. Roller - Use a 3/8" to 1-1/2" nap cover. Spray - Airless Pressure 2300 psi Tip028" Reduction ... as needed up to 1 pt/gal Remove all in-line and gun filters</p>	<p>WARNING! Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at 1-800-424-LEAD (in US) or contact your local health authority.</p> <p>Masonry, Concrete, Cement, Block Remove all surface contamination, form release agents, moisture curing membranes, etc. by washing with an appropriate cleaner, rinse and allow to dry. Pressure wash the surface if needed. Remove existing peeled or checked paint to a sound surface. Concrete and mortar must be cured, generally 30 days, at 75°F before painting.</p> <p>Complete removal of sealers, release compounds, and to provide a profile, tilt-up and poured-in-place concrete could require sandblasting or cleaning with commercial detergents. Do not apply to smooth, slick surfaces, peeling may result.</p>
<p>PrepRite Block Filler meets or exceeds the criteria set forth by the U. S. Green Building Council LEED-CI, Version 2.0 and LEED-NC Version 2.2. All results have been verified by our ISO 9001 Laboratory.</p>	<p>Spray application may be backrolled to work material into the surface. All application methods may be squeegeed to provide a very smooth surface.</p>	<p>Masonry surfaces must be dry before priming. Moisture content must be 15% or lower, and the pH between 6 and 9. If the pH is greater than 9, use Loxon Block Surfacer in place of PrepRite Block Filler.</p> <p>For repairing exterior cracks, bugholes, air pockets, and other voids use ConSeal™ Patches and Sealants.</p>

107.10

PREPRITE®

BLOCK FILLER

INTERIOR/EXTERIOR LATEX

B25W25



**SHERWIN
WILLIAMS.**

SURFACE PREPARATION

Mildew

Remove before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

CLEANUP INFORMATION

Clean spills and spatters immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment. Follow manufacturer's safety recommendations when using mineral spirits.

CAUTIONS

Do not apply at temperatures below 50°F. Protect from freezing.

LABEL CAUTIONS

CAUTION contains CRYSTALLINE SILICA. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water. Get medical attention if irritation persists. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. WARNING: This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.
HOTW 04/10/2006 B25W0025 16 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.