



Adhesion Test Report

JOB NAME: DuPont Exterior Painting	DATE: 08/4/2010
	PERSON RESPONSIBLE: Russ Phillips

NAME OF COATING: Imron Industrial Strength Urethane over Corlar 2.1 Epoxy Primer	WFT REQUIRED: 4-5 Mils
Cure Time: 7 Days	

Initial Reading: At 3 Days From Application	TIME: July 26, 2010
----------------------------------------------------	----------------------------

Urethane removed from metal substrate. Some epoxy primer was also removed. Test performed 4 days prior to full cure.



Intermediate Reading: At 5 Days From Application	TIME: July 28, 2010
---------------------------------------------------------	----------------------------

Urethane removed from epoxy primer. Epoxy primer shows good adhesion. Test performed 2 days prior to full cure.



Final Reading At 10 Days From Application	TIME: August 2, 2010
--------------------------------------------------	-----------------------------

Urethane and epoxy primer show good adhesion. Test performed after full cure.

Adhesion Test Result: PASS

